

Product	Effective Density [g/cm ³]	Average Particle size [μm]	Particle Size [μm] (Malvern)	Pressure Resistance Isostatic [Psi]	Pressure Resistance Isostatic [Mpa]
Q-CEL[®] 300	0.21	90	5 - 200	500	3.4
Q-CEL[®] 6014	0.14	85	5 - 200	250	1.7
Q-CEL[®] 6019	0.19	75	5 - 175	500	3.4
Q-CEL[®] 6019S	0.19	70	5 - 150	500	3.4
Q-CEL[®] 6020FPS	0.2	45	5 - 90	500	-
Q-CEL[®] 6717	0.19	52	5 - 105	500	3.4
Q-CEL[®] 5028	0.25	75	5 - 120	750	5.2
Q-CEL[®] 6028	0.28	70	5 - 150	750	-
Q-CEL[®] 6036	0.36	60	5 - 125	1,000	6.8
Q-CEL[®] 6042S	0.42	50	5 - 90	2,000	13.8
Q-CEL[®] 6048	0.48	50	5 - 100	3,000	20.7
Q-CEL[®] 5070S	0.7	35	10 - 100	3,500	24.2
Q-CEL[®] 5019	0.19	72	5 - 150	500	-
Q-CEL[®] 5032S	0.32	63	5 - 150	1,000	-
Q-CEL[®] 7019	0.19	80	5 - 150	500	3.4
Q-CEL[®] 7023S	0.23	85	5 - 120	750	5.2
Q-CEL[®] 7028	0.27	75	5 - 120	1,000	-
Q-CEL[®] 7036	0.36	63	5 - 125	1,000	-
Q-CEL[®] 7040S	0.4	54	5 - 100	2,000	13.8

The stated values correspond to typical values and hence do not represent a specification.